



# BASYPOL Mgo

Chrome Basifying Agent

<b>Chemical composition</b>	Blend of Inorganic compounds
<b>Activity</b>	98%
<b>Appearance</b>	White powder
<b>Solubility</b>	Sparingly soluble in weak acid solutions
<b>Shelf life</b>	Up to 1 year at temperatures between 5 and 40° C.
<b>Dilution</b>	Added Undiluted

## Field of application

For the basification of chrome in chrome tanning.

## Properties

BASYPOL Mgo being blend of special Inorganic compounds is an effective basifying agent .

BASYPOL Mgo provides Wet Blue with uniform pleasant colour.

Avoids lot to lot variation of colour.

BASYPOL Mgo catalyses with the chrome in the bath gradually and consistantly and makes the chrome complex enter the leather gradually thereby avoiding looseness and sugariness.

## Application:

BASYPOL Mgois applied after through and through penetration of chrome and after the running time of Basic Chromium Sulfate.

BASYPOL Mgo is added undiluted but the bath is disturbed very frequently in order to get penetration.

## Quantities:

Depending upon end pickle pH requirement a dosage of 0.3% to 0.75% will be enough.

To achieve pH 4.0 it is adviced to run 5 to 6 hours.

his information and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to check its validity and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with our General Conditions of Sale and Delivery.

**ZSIVIRA CHEMIE MERK PRIVATE LIMITED**

10/10