



ZEPROLIN GW

Polymerised sequestrant

Chemical composition	Polymer condensated with sequestrants
Activity	ca. 98 %
Appearance	Pale White free flowing Hygroscopic powder
pH - value 1 : 10	7.5 – 8.5
Charge	anionic
Shelf life	Up to 1 year at temperatures between 5 and 40° C.
Dilution	Added Undiluted

Field of application

Multifunctional use from raw to dyeing.

Properties

ZEPROLIN GW provides Even and Deep Penetration of dyes and avoids dye patches .

Provides full uptake of fatliquors and syntans .

Reduces the water hardness predominantly thereby helps uptake of all tanning auxiliaries.

Provides even shade with lustre for Suedes and Drum Dyed Leathers.

Provides inner softness with roundness even in thick leathers.

Quantities:

In Chrome Tanning: 0.5% to 1.5% ZEPROLIN GW

In Retanning & Fatliquoring: 0.5% to 1.5% ZEPROLIN GW

In Dyeing : 0.5% to 1% ZEPROLIN GW

This information and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to check its validity and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with our General Conditions of Sale and Delivery.

ZSIVIRA CHEMIE MERK PRIVATE LIMITED

03/11