



ZSIVIROL B3M

Ester Based Fatliquor

Chemical composition	Blend of Fatty esters
Fattening substance	ca. 60 %± 2%
Appearance	Reddish oil
pH - value 1 : 10	5.0 – 6.0
Charge	Anionic
Stability to electrolytes	Stable to acids and salts under usual tannery conditions. Stable in chrome liquors
Shelf life	Up to 1 year at temperatures between 5 and 40° C.
Dilution	Combinations with other fatliquors have to be stirred thoroughly before dilution. dilution method: 1 : 3 with water of 50 - 60° C.

Field of application

In the chrome tanning and retanning, in the main fatliquor.

Properties

Excellent light fastness

Extreme softness with light weight

Gives waxy touch and silky feel.

Excellent fullness with body and inner sponginess.

Application:

ZSIVIROL B3M is mainly used in the main fatliquoring bath for soft gloving, garment and upholstery leather where ever extreme softness is needed.

Quantities:

Can be used as a single fatliquor upto 20% to achieve very high softness.

However as the product is compatible with all the normal fatliquors and auxiliaries, the quantity of usage depends on the individual requirement of the article.

Note : The product being combination of various raw materials, there are Chances of variations in colour and viscosity. The property and Application of the product will remain same.

This information and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to check its validity and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with our General Conditions of Sale and Delivery.

ZSIVIRA CHEMIE MERK PRIVATE LIMITED

02/13