



ZSIVIROL LON

Lanolin Fatliquor

Chemical composition	Formulation of synthetic oils with Lanolin
Fattening substance	ca. 60 %
Appearance	Reddish Brown Oil
pH - value 1 : 10	6 - 7
Charge	Anionic
Stability to electrolytes	Highly stable to acids and salts under usual tannery conditions.
Shelf life	Up to 1 year at temperatures between 5 and 40° C.
Dilution	Combinations with other fatliquors have to be stirred thoroughly before dilution. dilution method: 1 : 3 with water of 50 - 60° C.

Field of application

For the production of garments and shoes.

Properties

Good softness.
Improves grain resilience.
Smooth grain.
Fullness.
Doesnot load the leather.

Application:

ZSIVIROL LON can be used alone or in combination with other fat liquors.

Quantities:

Retanned Chrome Leather : upto 6%

Note : The product being combination of various raw materials, there are Chances of variations in colour and viscosity. The property and Application of the product will remain same.

This information and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to check its validity and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with our General Conditions of Sale and Delivery.

ZSIVIRA CHEMIE INDIA PRIVATE LIMITED

02/2010