

ZSIVIROL MLi-N

Synthetic Fatliquor

Blend of Synthetic Oils & sperm substitutes
ca. 60 %
Reddish oil
6.0 - 7.0
Anionic
Stable to acids and salts under usual tannery conditions. Stable in chrome liquors
Up to 1 year at temperatures between 5 and 40° C.
Combinations with other fatliquors have to be stirred thoroughly before dilution. dilution method: 1:3 with water of 50 - 60° C.

Field of application

In the chrome tanning and retanning, in the main fatliquor.

Properties

Good light fastness Very high softness Gives waxy touch and silky feel. Excellent fullness with body.

Application:

ZSIVIROL MLIN is mainly used for soft, gloving, garment and upholstery leather in the main fatliquoring bath.

Quantities:

Garment leather sheep 7.0 - 10,0 % ZSIVIROL MLiN

2.0 - 3.0 % ZSIVIROL LNM

Cattle Clothing leather: 3.0% to 5.0% ZSIVIROL LECi.

6.0% - 8.0% ZSNIROL MLiN

Goat skins: 2% to 3% ZSIVIROL LECi.

8 % to 10% ZSIVIROL MLiN

Cattle Upholstery: 10% to 14% ZSIVIROL MLiN

Note: The product being combination of various raw materials, there are Chances of variations in colour and viscosity. The property and Application of the product will remain same.

This information and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to check its validity and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with our General Conditions of Sale and Delivery.

ZAVIRA CHEMIE MERIC PRIVATE UMITED

02/10