



ZSIVITAN WE

Veg Syntan

| | |
|-----------------------------|---|
| Chemical composition | Blend of Natural and organic tannins |
| Activity | ca. 95% |
| Appearance | Light tan powder |
| pH - value 1 : 10 | 5.5 – 6.5 |
| Charge | anionic |
| Shelf life | Up to 1 year at temperatures between 5 and 40° C. |
| Dilution | Added Undiluted |

Field of application

In the retanning of neutralised leather and more specifically for shoe uppers.

Properties

Gives tight leather with firm grain.

Good filling properties

Allows an even dyeing with brilliant shades.

Application:

ZSIVITAN WE is applied on neutralized leathers alone or along with other syntans or vegetable tannins.

Quantities:

In the Shoe Upper: 3 to 6 % ZSIVITAN WE

Corrected grain leather: 3% to 4% ZSIVITAN WE
4% to 6% MIMOSA

garment leather: 2% to 4% ZSIVITAN WE

This information and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to check its validity and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with our General Conditions of Sale and Delivery.

ZSIVIRA CHEMIE MERK PRIVATE LIMITED

01/10