



ZSIVITAN 2AN

Amphoteric Syntan

Chemical composition	Aromatic Condensation Product
Activity	ca. 96 %
Appearance	Creamish powder
pH - value 1 : 10	3.5 – 4.5
Charge	Amphoteric
Shelf life	Up to 1 year at temperatures between 5 and 40° C.
Dilution	Added Undiluted

Field of application

Re-tanning and filling of all types of chrome and semi-chrome leathers.

Properties

ZSIVITAN 2AN being amphoteric special syntan can be used in all stages of rechroming and retanning.

ZSIVITAN 2AN produces leathers of light weight, smooth grain with soft feel.

ZSIVITAN 2AN is best for production of smooth nappa, nubuck and suedes.

ZSIVITAN 2AN enhances the filling action of vegetable extracts.

ZSIVITAN 2AN provides uniform dyeability both on grain and flesh side and improves dye intensity to the leather.

Application:

ZSIVITAN 2AN is applied alone or in combination with vegetable/ synthetic tanning agents.

Usage Quantities:

Cow nappa: 2 to 3 % ZSIVITAN 2AN

Sheep nappa: 3 to 4% ZSIVITAN 2AN

Nubuck : 3 to 4 % ZSIVITAN 2AN

Note:

AS THE PRODUCT IS THE COMBINATION OF MANY RAW MATERIALS, THE COLOUR OF THE PRODUCT MAY SLIGHTLY VARY FROM TIME TO TIME. BUT THE TECHNICAL ASPECT OF THE PRODUCT WILL REMAIN SAME AT ALL TIMES.

The information in this leaflet and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty. and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to check its validity and to test our products as to their suitability for the intended processes and uses. The application and use of our products in your production system eventhough it is on the basis of our technical advice are beyond our control as the raw material you use may vary from time to time and, therefore, our products are used entirely under your own responsibility. Our products are in accordance with our General Conditions of Sale and Delivery.

ZSIVIRA CHEMIE MERK PVT LIMITED