



ZSIVITAN 2MH

Melamine Resin Syntan

Chemical composition	Melamine condensation product
Activity	ca. 97 %
Appearance	Pale White powder
pH - value 1 : 10	6 – 6.5
Charge	Anionic
Shelf life	Up to 1 year at temperatures between 5 and 40° C.
Dilution	Added Undiluted

Field of application

Re-tanning and filling of chrome tanned and semi-chrome leathers

Properties

Specially fills the loose parts of the leather

Improves the buffing properties

Good Light fastness.

Produce soft leather with a full handle and firm grain.

Application:

ZSIVITAN 2MH is added together with other syntans or vegetable tannins.

Usage Quantities:

Full grain upper leather: 3 to 4 % ZSIVITAN 2MH

Corrected grain upper leather: up to 6% ZSIVITAN 2MH

Garment leathers 2 to 3 % ZSIVITAN 2MH

Suede crusting
(Garment & shoe) 2 to 4% ZSIVITAN 2MH

Note:

AS THE PRODUCT IS THE COMBINATION OF MANY RAW MATERIALS, THE COLOUR OF THE PRODUCT MAY SLIGHTLY VARY FROM TIME TO TIME. BUT THE TECHNICAL ASPECT OF THE PRODUCT WILL REMAIN SAME AT ALL TIMES.

This information and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to check its validity and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with our General Conditions of Sale and Delivery.

ZSIVIRA CHEMIE MERIK PRIVATE LIMITED

01/10