



# ZSIVITAN 2M

Dicyandiamide Resin Syntan

<b>Chemical composition</b>	Dicyandiamide condensation product
<b>Activity</b>	ca. 95 %
<b>Appearance</b>	Pale creamish powder
<b>pH - value 1 : 10</b>	8.5 – 9.0
<b>Charge</b>	Anionic
<b>Shelf life</b>	Up to 1 year at temperatures between 5 and 40° C.
<b>Dilution</b>	Added Undiluted

## Field of application

Re-tanning and filling of all types of chrome leather

## Properties

**Specially fills the loose parts of the leather like shoulder, belly & flanks.**

**Provides even fullness throughout the leather.**

**Good Light fastness.**

**Produce soft leather with a full handle and firm grain.**

**Improves buffing properties.**

## Application:

ZSIVITAN 2 M is added together with other syntans or vegetable tannins.

## Usage Quantities:

Full grain upper leather: 3 to 5 % ZSIVITAN 2M

Corrected grain upper leather: 2 to 5% ZSIVITAN 2M

Split Suedes 2 to 4 % ZSIVITAN 2M

**Upholstery** 2 to 4% ZSIVITAN 2M

## Note:

AS THE PRODUCT IS THE COMBINATION OF MANY RAW MATERIALS, THE COLOUR OF THE PRODUCT MAY SLIGHTLY VARY FROM TIME TO TIME. BUT THE TECHNICAL ASPECT OF THE PRODUCT WILL REMAIN SAME AT ALL TIMES.

This information and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to check its validity and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with our General Conditions of Sale and Delivery.

**ZSIVIRA CHEMIE MERK PRIVATE LIMITED**

01/10