ZSIVITAN DL

Sulfone Based Syntan

Chemical composition	Aromatic Sulfone Condensation Product
Activity	ca. 95 %
Appearance	Whitish powder
pH - value 1 : 10	3.0 – 4.5
Charge	Anionic
Shelf life	Up to 1 year at temperatures between 5 and 40° C.
Dilution	Added Undiluted

Field of application
In the Re-tanning of neutralised leather.

Properties
Provides soft leather fullness and fine grain.
Excellent filling properties.
Allows even dyeing with brilliant shades.
Ensures light and uniform colours in combination with vegetable tannins.
Best suitable for E I leathers.

Application:
ZSIVITAN DL is applied alone or in combination with vegetable/synthetic tanning agents on neutralised leathers..

Usage Quantities In Retanning of Neutralised leathers:

Corrected grain leather :	3 to 4 % ZSIVITAN DL 4 to 6% Mimosa
Softy Upper leather:	2 to 3% ZSIVITAN DL

Note:

AS THE PRODUCT IS THE COMBINATION OF MANY RAW MATERIALS, THE COLOUR OF THE PRODUCT MAY SLIGHTLY VARY FROM TIME TO TIME. BUT THE TECHNICAL ASPECT OF THE PRODUCT WILL REMAIN SAME AT ALL TIMES.

The information in this leaflet and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty. and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to check its validity and to test our products as to their suitability for the intended processes and uses. The application and use of our products in your production system eventhough it is on the basis of our technical advice are beyond our control as the raw material you use may vary from time to time and, therefore, our products are used entirely under your own responsibility. Our products are in accordance with our General Conditions of Sale and Delivery.

ZSVIRA CHEMIE MERK PRIVATE LIMITED