



ZSIVITAN FCBE - T

Bleaching Syntan

Quantities:

In Vegetable / EI tanning – 3 to 5%

Chemical composition	Naphthalene Sulfonic Acid Condensate
Aluminium Oxide content	90 %
pH - value 1 : 10	1.2 – 1.8
Charge	Cationic
Appearance	Pale White Powder
Shelf life	Up to 6 months at temperatures between 5 and 40° C.
Dilution	Added to drum directly

Field of application

As bleaching syntan for vegetable tanned/EI tanned leather.

Properties

ZSIVITAN FCBE - T provides excellent bleaching on Vegetable / EI tanned and retanned leathers.

ZSIVITAN FCBE – T provides leather with even pale shade with high light fastness.

ZSIVITAN FCBE – T reacts with Iron III Oxide in leather or drum bath and helps to avoid Iron Stain formation.

This information and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to check its validity and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with our General Conditions of Sale and Delivery.

ZSIVIRA CHEMIE MERK PRIVATE LIMITED

01/10