



ZSIVITAN MS

Steryne Meleic Syntan

Chemical composition	Steryne Maleic –acrylic copolymer
Solids	30%
Appearance	Clear to Pale liquid
pH - value 1 : 10	5.5 – 6.5
Charge	anionic
Shelf life	Up to 1 year at temperatures between 5 and 40° C.
Dilution	Added Undiluted

Field of application

In the retanning of chrome and semi-chrome tanned leather.

Properties

Gives a very fine and tight grain when used before neutralization..

When used after neutralization it provides leather with excellent dry drummable property thereby producing even break.

Allows an even dyeing with good light fastness

Application:

ZSIVITAN MS can be applied alone or along with vegetable and other synthetic tannins.

Quantities:

In the Shoe Upper:	2 to 6 % ZSIVITAN MS
Upholstery leather:	2% to 6% ZSIVITAN MS
Bovine garment leather:	2% to 3% ZSIVITAN MS
Sheep Garment :	3 to 4% ZSIVITAN MS

This information and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to check its validity and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with our General Conditions of Sale and Delivery.

ZSIVIRA CHEMIMERK PRIVATE LIMITED

01/09