



Smart Chemistry

ZSIVIRA

ZSIVITAN RP Liq

Polymerised Phenol

Chemical composition	<i>Phenol with Polymer Condensate</i>
Solids	<i>40 to 45%</i>
Appearance	<i>Reddish Brown Liquid</i>
pH - value 1 : 10	<i>3.5 – 4.5</i>
Charge	<i>Anionic</i>
Shelf life	<i>Up to 1 year at temperatures between 5 and 40° C.</i>
Dilution	<i>Added Undiluted</i>

Field of application :

In all type of leathers where fullness good filling without looseness in the mainly needed.

Properties :

- *Excellent filling in loose portion. Hence no grain disturbance.*
- *Provides excellent fullness and mellowness.*
- *Good Print retention with light weight.*
- *Provides even grain.*

The above information on application on leather is given in accordance to the best of our knowledge and our lab applications. As the usage of the product by the consumer is not under our control, we are not liable for any sort of claims or reimbursements. The product is given without any guarantee/warranty in connection to end use.

ZSIVIRA CHEMIE MERK PRIVATE LIMITED

www.zsiviraindia.com info@zsiviraindia.com



ZSIVIRA

ZSIVITAN RP Liq

Polymerised Phenol

Usage Quantity :

<i>In Sheep Nappa</i>	<i>: Upto 6%</i>
<i>In Cow Softies</i>	<i>: Upto 6%</i>
<i>In Goat Gloving</i>	<i>: Upto 4%</i>
<i>In EI Tanning</i>	<i>: Upto 4%</i>
<i>In Shoe Upper</i>	<i>: Upto 4%</i>

Note : The product being combination of various raw materials, there are chances of variations in colour and viscosity. The property and Application of the product will remain same.

The above information on application on leather is given in accordance to the best of our knowledge and our lab applications. As the usage of the product by the consumer is not under our control, we are not liable for any sort of claims or reimbursements. The product is given without any guarantee/warranty in connection to end use.

ZSIVIRA CHEMIE MERK PRIVATE LIMITED

www.zsiviraindia.com info@zsiviraindia.com