



# ZSIVIRA

## CATAZYME JT

*Enzymatic Acid Bate*

<b>Chemical composition</b>	<b>Blend of Enzymes</b>
<b>Active pH</b>	<b>Active at pH 4.0 to 6.0</b>
<b>Appearance</b>	<b>Pale Beige to Off white powder</b>
<b>Active Temperature</b>	<b>Between 25 to 40° C.</b>
<b>Shelf life</b>	<b>Up to 1 year at temperatures if stored in closed containers at ambient temperature</b>
<b>pH 10%</b>	<b>7.0 to 7.5</b>

**Properties :**

*CATAZYME JT is a blend of Enzymes to give good softness to the leather.*

*Provides uniformity in grain pattern with fullness and softness.*

*Will not loosen the leather even in case of mistaken usage at higher quantities as it maintains the equilibrium between the leather and the tanning bath.*

*For Normal Leathers : (Increase pH to 4.0)*

	<b>% on Depickle</b>	<b>% on wet blue</b>	<b>Run Time</b>
<b>Goat Skins</b>	<b>Upto 3.0%</b>	<b>Upto 5.0%</b>	<b>90 – 120 minutes</b>
<b>Sheep Skins</b>	<b>Upto 2.0%</b>	<b>Upto 5.0%</b>	<b>45 minutes</b>
<b>Calf Skins</b>	<b>Upto 3.0%</b>	<b>Upto 5.0%</b>	<b>90 – 120 minutes</b>
<b>Cattle Hides</b>	<b>Upto 3.0%</b>	<b>Upto 5.0%</b>	<b>90 – 120 minutes</b>

*To get the best softness along with area increase it is strongly recommended to use enzyme accelerator ZEPROLIN ZXi / TMZ for about 2% along with CATAZYME JT.*

The above information on application on leather is given in accordance to the best of our knowledge and our lab applications. As the usage of the product by the consumer is not under our control, we are not liable for any sort of claims or reimbursements. The product is given without any guarantee/warranty in connection to end use.

**ZSIVIRA CHEMIE MERK PRIVATE LIMITED**

www.zsiviraindia.com info@zsiviraindia.com